

About Lumiflon

gloss and color retention of tokiwa bridge



october 1988



april 1993



april 2007

initial gloss

75

final gloss

69

gloss retention

91%

color change

$\Delta E=3.5$